JÓŹWIAK
POZNAŃ

TECHNICAL DATA SHEET
VENTA

Modified on: 2017-11-20
Created on: 2017-11-20
Report number: JC17111522129

FABRIC DETAILS			
Composition:	Polyester / Viscose 52% / 48%		
Weight g/m:	131 g/m	Width:	145 cm
Weight g/m^2:	90 g/m2	Usable width:	143 cm
Weave:	-	Density:	-
	WARP	WEFT	
Yarn count:	-	-	

COLOUR FASTNESS		REFERENCE	COLOR CHANGE	STAIN					
				A	C	N	P	AC	W
To washing:		ISO 105-C06:2010	4-5	4-5	4-5	4-5	4-5	4-5	4-5
To dry cleaning:		ISO 105-D01:2010	4-5	4-5	4-5	4-5	4-5	4-5	4-5
To perspiration:	Acid	ISO 105-E04:2013	4-5	4-5	4-5	4-5	4-5	4-5	4-5
	Alcalic	ISO 105-E04:2013	4-5	4-5	4-5	4-5	4-5	4-5	4-5
				WARP			WEFT		
To dry rubbing:		ISO 105-X12:2016		4-5			4-5		
To wet rubbing:		ISO 105-X12:2016		4-5			4-5		
			COLOUR CHANGE AT ONCE	COLOUR CHANGE AFTER 4 HOURS			STAINING ON COTTON ADJACENT		
To hot pressing	Dry	ISO 105-X11:1994	4-5	4-5					
	Damp	ISO 105-X11:1994	4-5	4-5			4-5		
	Wet	ISO 105-X11:1994	4-5	4-5			4-5		
To non-chlorine bleach:		AATCC TS-001	4,5						
To light:		ISO 105-B02:2014	above 4						

A - acetate C - cotton N - nylon P - polyester AC - acrylic W - wool

CARE INSTRUCTION		REFERENCE	COLOR	PILING	DEFECTS	CONCLUSION
Appearance after washing:	After one wash	ISO 6330:2012	4-5	4-5	No defects	General appearance satisfactory
	After three washes	ISO 6330:2012	4-5	4-5	No defects	General appearance satisfactory
Appearance after dry cleaning:		ISO 3175-2:2010	4-5	4-5	No defects	General appearance satisfactory
Care pictograms:						

PACKING			
Roll lenght:	~ 50 m	Wrapping:	Carton tubes inside, polybags & woven bags outside; each packing layer labelled

HS customs code:	5515119000

JÓŹWIAK S.C.
Przewozowa 3, PL-62064 Plewiska / Poznań, Polska
VAT: PL7792295976 / REGON: 300419818
T: +48 61 867 75 14 / F: +48 61 867 80 65
jozwiak@jozwiak.eu / www.jozwiak.eu

JÓŹWIAK
POZNAŃ

TECHNICAL DATA SHEET
VENTA

PHYSICAL PROPERTIES		REFERENCE	WARP						WEFT
Seam slippage:	Seam opening at 6mm	ISO 13936-1:2004	X						181 N
	Seam strenght	ISO 13936-1:2004	160 N (FBS)						> 200 N (YPO)
Dimensional stability to washing:		ISO 3758:2011/ISO 5077:2007/ISO 6330:2012	-0,3 %						-3,1 %
Dimensional stability to dry cleaning:		ISO 3175-2:2010	-0,4 %						-0,8 %
Dimensional stability to steam:		ISO 3005:1978	-0,7 %						-0,4 %
Tear strenght:		ISO 13937-2:2000	Cross Tear						15 N
Tensile strenght:		ISO 13934-2:2014	700 N						250 N
Elongation:		ISO 13934-2:2014	26,5 %						25,3 %
			CYCLES						
			125	500	1000	2000	5000	7000	10800
Pilling:		ISO 12945-2:2000	4-5	4-5	4-5	4-5	4-5	4-5	-
			Elongation	UN (1min)	UN (30min)	RE (1min)	RE (30min)		
Stretch properties:	Warp	EN14704-1:2005	-	-	-	-	-		
	Weft	EN14704-1:2005	-	-	-	-	-		
	Length - specified load	EN14704-1:2005	-	-	-	-	-		
	Width - specified load	EN14704-1:2005	-	-	-	-	-		
	Length - specified elongation	EN14704-1:2005		-	-	-	-		
	Width - specified elongation	EN14704-1:2005		-	-	-	-		
Spirality:	After drycleaning	ISO 3175-2:2010	0,0 %						
	After laundering	ISO 16322-2:2005	0,0 %						
Abrasion resistance:		ISO 12947-2:2016	> 30000 Cycles						

FB - Fabric Broken STB - Sewing Thread Broken FBS - Fabric Broken at Seam YPO - Yarn Pull Out UN - Unrecovered Elongation RE - Recovered Elongation
X - The Seam Opening was less than 6mm, though the ultimate steam strenght was founded as stated Cross Tear - means the force does not proceed along the direction of force

JÓŹWIAK S.C.
Przewozowa 3, PL-62064 Plewiska / Poznań, Polska
VAT: PL7792295976 / REGON: 300419818
T: +48 61 867 75 14 / F: +48 61 867 80 65
jozwiak@jozwiak.eu / www.jozwiak.eu