


## TECHNICAL DATA SHEET MARRON/KASHMIR BLUE

Modified on: 2022-09-29  
Created on: 2021-12-28  
Report number: TG21061276X1  
TG22035835X1

FABRIC DETAILS			
Composition:	Polyester / Viscose / Elastane 78% / 20% / 2%		
Weight g/m:	300 g/m	Width:	150 cm
Weight g/m <sup>2</sup> :	200 g/m <sup>2</sup>	Usable width:	147 cm
Weave:	Twill	Density:	101*100
		WARP	WEFT
Yarn count:			-

COLOUR FASTNESS		REFERENCE	COLOR CHANGE	STAIN					
				A	C	N	P	AC	W
To washing:		ISO 105-C06:2010	4-5	4-5	4-5	4-5	4-5	4-5	4-5
To dry cleaning:		ISO 105-D01:2010	4-5	4-5	4-5	4-5	4-5	4-5	4-5
To perspiration:	Acid	ISO 105-E04:2013	4-5	4-5	4-5	4-5	4-5	4-5	4-5
	Alcalic	ISO 105-E04:2013	4-5	4-5	4-5	4-5	4-5	4-5	4-5
				WARP			WEFT		
To dry rubbing:		ISO 105-X12:2016		4-5			4-5		
To wet rubbing:		ISO 105-X12:2016		4			4		
			COLOUR CHANGE AT ONCE	COLOUR CHANGE AFTER 4 HOURS		STAINING ON COTTON ADJACENT			
To hot pressing	Dry	ISO 105-X11:1994	4-5	4-5					
	Damp	ISO 105-X11:1994	4-5	4-5		4			
	Wet	ISO 105-X11:1994	4-5	4-5		4			
To non-chlorine bleach:		AATCC TS-001		4-5					
To light:		ISO 105-B02:2014		4					

A - acetate C - cotton N - nylon P - polyester AC - acrylic W - wool

CARE INSTRUCTION		REFERENCE	COLOR	PILING	DEFECTS	CONCLUSION
Appearance after washing:	After one wash	ISO 6330:2012	4-5	4-5	No defects	General appearance satisfactory
	After three washes	ISO 6330:2012	4-5	4-5	No defects	General appearance satisfactory
Appearance after dry cleaning:		ISO 3175-2:2010	4-5	4-5	No defects	General appearance satisfactory
Care pictograms:						

PACKING			
Roll length:	~ 50 m	Wrapping:	Carton tubes inside, polybags & woven bags outside; each packing layer labelled

HS customs code:	5515119000
------------------	------------

### JÓŹWIĄK S.C.

Przewozowa 3, PL-62064 Plewiska / Poznań, Polska  
VAT: PL7792295976 / REGON: 300419818

T: +48 61 867 75 14 / F: +48 61 867 80 65  
jozwiak@jozwiak.eu / www.jozwiak.eu

## TECHNICAL DATA SHEET MARRON/KASHMIR BLUE

PHYSICAL PROPERTIES		REFERENCE	WARP				WEFT			
Seam slippage:	Seam opening at 6mm	ISO 13936-1:2004	X				X			
	Seam strenght	ISO 13936-1:2004	>200 N (STB)				>200 N (STB)			
Dimensional stability to washing:		ISO 3758:2011/ISO 5077:2007/ISO 6330:2021	-0,6 %				-1,0 %			
Dimensional stability to dry cleaning:		ISO 3759:2011/ISO 5077:2007, ISO 3175 2:2017	-0,4 %				-0,3 %			
Dimensional stability to steam:		ISO 3005:1978	-1,0 %				-2,6 %			
Tear strenght:		ISO 13937-2:2000	37 N				45 N			
Tensile strenght:		ISO 13934-2:2014	660 N				430 N			
Elongation:		ISO 13934-2:2014	24,6 %				43,9 %			
			CYCLES							
			125	500	1000	2000	5000	7000	10800	
Pilling:		ISO 12945-2:2000	4	4	4	3-4	3	3	-	
			Elongation		UN (1min)	UN (30min)	RE (1min)		RE (30min)	
Stretch properties:	Warp	EN14704-1:2005	-	-	-	-	-	-		
	Weft	EN14704-1:2005	-	-	-	-	-	-		
	Length - specified load	EN14704-1:2005	-	-	-	-	-	-		
	Width - specified load	EN14704-1:2005	-	-	-	-	-	-		
	Length - specified elongation	EN14704-1:2005	-	-	-	-	-	-		
	Width - specified elongation	EN14704-1:2005	-	-	-	-	-	-		
Spirality:	After drycleaning	ISO 3175-2:2010	0,0 %							
	After laundering	ISO 16322 2:2021	0,0 %							
Abrasion resistance:		ISO 12947-2:2016	> 30000 Cycles							

FB - Fabric Broken STB - Sewing Thread Broken FBS - Fabric Broken at Seam YPO - Yarn Pull Out UN - Unrecovered Elongation RE - Recovered Elongation  
X - The Seam Opening was less than 6mm, though the ultimate steam strenght was founded as stated Cross Tear - means the force does not proceed along the direction of force